



VINC

- Recommended for still wines with a shelf-life of up to 3 years



SENSORY PROPERTIES

Releasable TCA - TCA Taint Free ⁽¹⁾ (ISO 20752)

DIMENSIONAL PROPERTIES

Length (standard): 38 / 44 mm (+/- 0,5) | **AQL - 4,0** (ISO 9727-1; ISO 2859; ISO 16420)

Diameter (standard): 24 mm (+/- 0,3) | **AQL - 1,5** (ISO 9727-1; ISO 2859; ISO 16420)

PHYSICAL PROPERTIES

Granule size: 0,5 - 2,0 mm | **AQL - N.A.** (Internal Method)

Density: 245 - 305 kg/m³ | **AQL - 4,0** (ISO 9727-2; ISO 2859; ISO 16420)

Moisture content: 4 - 8 % | **AQL - 2,5** (ISO 9727-3; ISO 2859; ISO 16420)

Torsion: ≥22 daN.cm | **AQL - N.A.** (NP 2803-6; ISO 2859)

Extraction force ⁽²⁾: 20 - 40 daN | **AQL - N.A.** (ISO 9727-5; ISO 2859)

Oxidants: : N.D. | **AQL - N.A.** (Internal Method)

OTR ⁽³⁾ - 0,0020 ml/day

AVAILABLE WASHES AND CUSTOMIZATION



Natura

Printing to simulate natural cork features is available.

100% of our granules undergo the *Vapex*[®] process.

⁽¹⁾ Below 0,5 ng/L with AQL 0,65 between 0,5-1,0 ng/L | ⁽²⁾ Lots > 10.000 corks | ⁽³⁾ Oxygen transfer rate

N.D. - Not detectable | N.A. - Not applicable | AQL - Acceptable Quality Level

Edition: March 2019